

Product	Sinopec Class 6 Synthetic Brake Fluid
Summary	Product description Sinopec Class 6 Synthetic Brake Fluid has been formulated from glycol ether and borate ester with selected additives. It satisfies the following specifications: ISO 4925 Class 6, SAE J1704 (Low Viscosity), FMVSS No. 116 DOT 4. Due to the low deep temperature viscosity this fluid is especially recommended for very cold areas.

Applications

Sinopec Class 6 Synthetic Brake Fluid is suitable for use in:

- Hydraulic disc, drum and anti-skid brakes and clutch systems of all passenger cars and commercial vehicles that require ISO 4925 Class 6 performance synthetic fluid.

Caution: do not use where a mineral oil-based fluid or a DOT 5 silicone-based fluid is required.

Features and benefits

- High wet and dry equilibrium reflux boiling point (ERBP at least 260°C, WERBP at least 170°C) minimises vapour formation on braking at high-speed or high-load conditions and maintains the fluid's hydraulic properties, thus ensuring good braking performance.
- Borate ester in the formulation acts as a water scavenger and helps to maintain the boiling point during service, so maintaining the quality of braking performance as the fluid ages.
- Excellent fluidity, even at low temperatures in very cold areas, enables optimum braking performance.
- A buffered alkaline pH protects iron and steel-containing system components from acidic corrosion, ensuring long component life.
- Selected corrosion inhibitors protect aluminium, copper, zinc and tin-containing system components from corrosion, ensuring long life.
- Good compatibility with common seal materials used in braking systems minimises fluid leakage and reduces component wear caused by inadequate lubrication, ensuring good braking performance.
- Excellent thermal and oxidation stability properties prevent fluid breakdown and deposit formation, maximising fluid life and performance.
- Fully compatible with other brake fluids that meet the DOT 3 or DOT 4 specifications also compatible with DOT 5.1.

Product Data Sheet

Typical data

Sinopec Class 6 Synthetic Brake Fluid	
Equilibrium reflux boiling point (ERBP), °C, ISO 4925	268
Wet ERBP, °C, ISO 4925	177
Kinematic viscosity, ISO 4925	
cSt @ -40°C	682
cSt @ 100°C	2.010
pH, ISO 4925	8.0
Corrosion, 120 h @ 100°C, mass change of metal strips, mg/cm ² , ISO 4925	
tinned iron	0.00
steel	0.00
aluminium	0.00
cast iron	0.00
brass	0.03
copper	0.05
Zinc	0.02
Effect on rubber, ISO 4925	
styrene butadiene rubber (SBR) @ 120°C	
cup diameter increase, mm	0.75
hardness change, IRHD	7
ethylene propylene diene monomer (EPDM) @ 120°C	
volume change, %	3.50
hardness change, IRHD	3

These data are given as an indication of typical values, not exact specifications.

Industry and OEM specifications

Sinopec Class 6 Synthetic Brake Fluid meets the performance requirements of the following industry specifications:	
FMVSS No. 116	DOT 4
GB12981-2012 ¹	HZY6
ISO 4925	Class 6
SAE	J1704 (Low Viscosity)

¹ Note: 'GB' standards are the National Standards of the People's Republic of China.

Accuracy of information

Data provided in this PDS is typical and subject to change as a result of continuing product research and development. The information given was correct at the time of printing. The typical values given are subject to variations in the testing procedures and the manufacturing process may also result in slight variations. Sinopec guarantees that its lubricants meet any industry and OEM specifications referred to on this data sheet.

Sinopec cannot be held responsible for any deterioration in the product due to incorrect storage or handling. Information on best practice is available from your local distributor.

Product Data Sheet

Product and environmental safety

This product should not cause any health problems when used in the applications suggested and when the guidance provided in the Material Safety Data Sheet (MSDS) is followed. Please consult the MSDS for more detailed advice on handling; MSDSs are available from your local distributor. Do not use the product in applications other than those suggested.

As with all products, please take care to avoid environmental contamination when disposing of this product. Used oil should be sent for reclamation/recycling or, if not possible, must be disposed of according to relevant government/authority regulations.

Issued: August 2015

© Sinopec 2015